

LEXAN EXELL™ D ST SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN EXELL™ D ST sheet is a textured polycarbonate sheet with UV protection on both sides, offering excellent light diffusion without transparency. It has an excellent impact resistance, an excellent fire performance, ease of handling and installation and is an excellent candidate for wide variety of exterior and interior applications such as balcony and staircase glazing.

TYPICAL PROPERTY VALUES

| PROPERTY | TEST METHOD | UNITS | VALUE |
|--------------------------------------------------------------|----------------|-------------------|---------------------|
| PHYSICAL | | | |
| Density | ISO 1183 | g/cm ³ | 1.20 |
| Water absorption, 50% RH, 23 °C | ISO 62 | % | 0.15 |
| Water absorption, saturation, 23°C | ISO 62 | % | 0.35 |
| MECHANICAL | | | |
| Yield stress 50 mm/min | ISO 527 | MPa | >60 |
| Yield strain 50 mm/min | ISO 527 | % | 6 |
| Nominal strain at break 50 mm/min | ISO 527 | % | >100 |
| Tensile modulus 1 mm/min | ISO 527 | MPa | 2300 |
| Flexural strength 2 mm/min | ISO 178 | MPa | 90 |
| Flexural modulus 2 mm/min | ISO 178 | MPa | 2300 |
| IMPACT | | | |
| Charpy impact, notched 23°C, 3.0 mm | ISO 179/1eA | kJ/m ² | 75 |
| Izod impact, unnotched 23°C, 3.0 mm | ISO 180/1U | kJ/m ² | NB |
| Izod impact, notched 23°C, 3.0 mm | ISO 180/1A | kJ/m ² | 70 |
| THERMAL | | | |
| Vicat softening temperature, rate B/120 | ISO 306 | °C | 145 |
| Temperature of deflection under load (type A), 1.8 MPa, flat | ISO 75-2 | °C | 127 |
| Thermal conductivity | ISO 8302 | W/m.°C | 0.2 |
| Coefficient of linear thermal expansion, 23-55°C | ISO 11359-2 | 1/°C | 7x 10 ⁻⁵ |
| Ball pressure test 125 ±2°C | IEC 60695-10-2 | - | Pass |
| ELECTRICAL | | | |
| Volume resistivity | IEC 60093 | Ohm.cm | >10 ¹⁵ |
| Dielectric strength, in oil, 3.2 mm | IEC 60243-1 | kV/mm | 18 |
| FIRE RATINGS | | | |
| Building & Construction | | | |
| Europe | EN13501-1 | - | b,s,d0 (2-6mm) |

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC, Specialty Film & Sheet representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

™ Trademarks of SABIC.

CHEMICAL RESISTANCE

LEXAN EXELL D ST sheet has sufficient resistance to most chemical substances encountered in normal exterior use. In applications where the product will come into contact with aggressive chemicals, specific (application related) testing of the material is always advised. It is essential to check the compatibility before use.

PRODUCT AVAILABILITY

| | |
|-------------------------|----------------------------------------------|
| Product code: | LEXAN EXELL D ST |
| Standard gauge: | 3, 4, 5, 6, 8 mm |
| Standard width: | 1250 and 2050 mm |
| Standard length: | 3050 and 6100 mm |
| Textures: | Polished one side, pebble texture on reverse |
| Colors: | Clear, bronze |

Other colors/sizes are available by special request.

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

